

TREO %	Density	Tonnage	ZrO ₂ %	Nb ₂ O ₅ %	HfO ₂ %	BeO %	TREO %	HREO %	LREO %	HREO/TREO
Cut-off	t per m3	t x 1000								Ratio
1.20%	2.72	8,095	2.77	0.37	0.06	0.19	1.655	0.849	0.806	51
0.95%	2.72	36,359	2.17	0.24	0.05	0.12	1.164	0.511	0.653	44
0.579%	2.72	140,259	1.93	0.18	0.05	0.08	0.933	0.371	0.562	40

TREO %	Density	Tonnage	ZrO ₂ %	Nb ₂ O ₅ %	HfO ₂ %	BeO %	TREO %	HREO %	LREO %	HREO/TREO
Cut-off	t per m3	t x 1000								Ratio
1.20%	2.73	2,572	2.57	0.30	0.06	0.15	1.532	0.764	0.768	50
0.95%	2.72	14,421	2.02	0.21	0.05	0.09	1.109	0.465	0.644	42
0.579%	2.72	89,629	1.83	0.16	0.05	0.06	0.882	0.334	0.548	38